

TECHNOROOF N30 THERMAL INSULATION BOARDS

MW-EN 13162-T5- DS (70,-)-DS(23,90)- CS(10)30-TR7,5-PL(5)350 -WS-
WL(P)-MU1- RfF: A1



Non-flammable stone wool slabs made of basaltic and gabbroic rocks

Product Description

TECHNOROOF N30 is non-flammable, hydrophobized heat- and sound-insulating slabs made of mineral wool based on the basalt group rocks.

Scope of application:

TECHNOROOF N30 slabs are intended for use in civil and industrial construction as a heat-insulating layer in new construction and reconstruction of buildings and structures for different purposes.

As the single-layer thermal insulation or the top layer in two- or three-layer insulation with the arrangement of a "wet" or "dry" screed on the insulation surface.

Also, it is used as the bottom layer for two- or three-layer thermal insulation of roofs.

Storage:

Slabs should be stored packed and stacked on pallets divided by types and sizes. During the entire storage period, the material must be protected from atmospheric precipitation. The height of the stack of slabs should not exceed 3 m upon storage.

Packaging Details:

Polyethylene shrink wrap is used for packaging. The method of wrapping and fixing a packaging material must ensure the reliable and strong packaging of slabs, their protection during loading and unloading operations, transportation and storage.

The main physical and mechanical characteristics

Essential characteristics	Performance	Harmonized technical specification
Declared thermal conductivity at 10 °C, λ_D , W/m ² K	0,036	
Limit deviations Length, Width, mm	±2/±1,5 %	
Limit deviations of thickness, mm	T5	
Thickness, (with increments of 10 mm), mm	50-200	
Deviation from squareness, mm/m	< 5	
Deviation from flatness, mm	< 6	
Compressive stress at 10% deformation, kPa	CS(10)30	
Tensile strength perpendicular to faces, kPa	TR7,5	
Point Load, N	PL(5)350	EN 13162:2012 + A1:2015
Dimensional stability, %:		
-at specified temperature	DS(70,-) less than 1	
-under specified temperature (23oC) and humidity conditions (90%R.H.)	DS(23,90) less than 1	
Reaction to fire, euroclass	A1	
Water Absorption during Short/	WS less than 1	
Longterm Immersion kg/m ²	WL(P) less than 3	
Water vapour transmission, MU	MU1	
Dangerous Substances:	Does not include dangerous substances	